

## CLAIM LISTING AND AMENDMENTS

1. (Currently amended.) A fire-protection glass product having a heat shielding characteristic, comprising:
  - a plurality of fireproof glass plates;
  - a resin intermediate layer interposed between adjacent ones of said glass plates and made of a material selected from fluorocarbon ~~resin~~and resin and polyethylene terephthalate resin; and
  - a heat-ray reflection film formed on the surface of at least one of said glass plates, said heat-ray reflection film being made of a material consisting essentially of indium oxide containing tin, antimony oxide containing tin, tin oxide containing fluorine, and tin oxide containing antimony, and said film having a reflectance of 50% or more, 70% or more, and 80% or more, for light having a wavelength of 1500nm, 2500nm, and 3000nm, respectively, and an average transmittance of 60% or more and an average reflectance of 12% or more to 19% or less for visible rays.
2. (Original.) A fire-protection glass product as claimed in claim 1, wherein at least one of said fireproof glass plates is made of a heat-resistant transparent crystallized glass.
3. (Cancelled.)
4. (Previously presented.) A fire-protection glass product as claimed in claim 1, wherein said heat-ray reflection film is formed on at least one surface of at least one of said fireproof glass plates.
5. (Cancelled.)
6. (Original.) A fire-protection glass product as claimed in claim 1, wherein said heat-ray reflection film has a thickness between 1000Å and 15000Å.

7. (Cancelled.)

8. (Currently amended.) A fire-protection glass product as claimed in claim 1, said glass product have a double-glazing structure including an additional ~~[[glas]]~~ glass plate attached through an air layer.

9. (Currently amended.) A fire-protection glass product having a heat shielding characteristic, comprising:

two fireproof glass plates;

a resin intermediate layer interposed between said glass plates and made of a material of fluorocarbon resin;

a heat-ray reflection film formed on the surface of at least one of said glass plates, made of a material consisting essentially of indium oxide containing tin, antimony oxide containing tin, tin oxide containing fluorine, and tin oxide containing antimony, and having a thickness between 1000Å and 15000Å, and having a reflectance of 50% or more for light having a wavelength of 1500nm, a reflectance of 70% or more for light having a wavelength of 2500nm, and a reflectance of 80% or more for light having a wavelength of 3000nm.

10. (Previously presented.) A fire-protection glass product as claimed in claim 9, wherein at least one of said fireproof glass plates is made of a heat-resistant transparent crystallized glass.

11. (Previously presented.) The fire-protection glass product of claim 9, wherein said film has an average reflectance of about 15% for visible light.

12. (Previously presented.) The fire-protection glass product of claim 10, wherein said film has an average reflectance of about 15% for visible light.